

WŁÓKNINY SYNTETYCZNE

| typ | foto | klasa | grubość [mm] | nominalna przepustowość [m ³ /h/m ²] | średnia skuteczność [Am%][Em%] | opór początkowy [Pa] | zalecany opór końcowy [Pa] | chłonność pyłowa [g/m ²] |
|-----------|---|-------|--------------|---|--------------------------------|----------------------|----------------------------|--------------------------------------|
| T150 |  | G2 | 10 | 5400 | 71,20% | 12 | 250 | 526,0 |
| T150/140 |  | G2 | 12 | 5400 | 76,30% | 21 | 250 | 387,0 |
| MSB130 |  | G3 | 5 | 5400 | 82,10% | 26 | 250 | 237,0 |
| MSB160 |  | G3 | 6 | 5400 | 88,20% | 30 | 250 | 284,7 |
| T209S140 |  | G3 | 14 | 5400 | 85,50% | 35 | 250 | 370,0 |
| T209SV140 |  | G3 | 14 | 5400 | 87,50% | 35 | 250 | 400,0 |
| PS305 |  | G3 | 25 | 5400 | 86,00% | 31 | 400 | 487,0 |
| T350 |  | G3 | 20 | 5400 | 87,20% | 30 | 250 | 562,0 |
| RBW200 |  | G3 | 10 | 7200 | 85,90% | 54 | 200 | 346,2 |
| NGB290/4 |  | G4 | 20 | 5400 | 91,20% | 40 | 250 | 490,0 |
| T500 |  | G4 | 22 | 5400 | 92,40% | 46 | 250 | 522,0 |
| NF400P |  | G4 | 20 | 900 | 95,70% | 20 | 400 | 290,0 |
| NF300/1 |  | F5 | 20 | 900 | 97,10% 45,60% | 27 | 450 | 284,7 |
| NF600PS |  | F5 | 22 | 900 | 95,40% 43,90% | 26 | 450 | 326,5 |